

# OPALJET DREAM 2 0W30

100% SYNTHETIC OIL FOR EURO 6 ENGINES

110027/01.24

Rev. 5

## DESCRIPTION & APPLICATIONS

OPALJET DREAM 2 is developed to meet the highest standards for modern engines.

OPALJET DREAM 2 ensures perfect protection and increases the life of mechanical parts.

OPALJET DREAM is developed to secure and enhance the fuel economy in Stellantis engines where an ACEA C2 or SPI SN 0W30 is advised.

Approvals

PSA B71 2302

PSA B71 2312-2022

## ADVANTAGES

- The 0W30 grade protects your engine when starting in extreme cold conditions (- 35 °C) and also offers significant fuel savings.
- Protects particulate filters against clogging due to its very low content of sulfur and sulfated ash.
- Very high shear strength and low volatility.

## PERFORMANCES

Satisfies to the following specifications:

ACEA C2-12

API SP

FIAT 9.55535-S1/G1

PSA B71 2302/2312-2022

## ENVIRONMENT, HEALTH & SAFETY

Please consult also the Safety Data Sheet about how to manipulate and to stock the product as well as to learn about the first aid measurements in case of accident.

Elimination after use must be made in conformity with the local rules in force about used oils disposal.

When needed, Safety Data Sheet can be obtained upon request.

Conservation of the product: 3 year(s) in closed container and sheltered.

# OPALJET DREAM 2 0W30

## PROPERTIES

| CHARACTERISTICS              | UNITS                    | METHODS     | TYPICAL DATA |
|------------------------------|--------------------------|-------------|--------------|
| SAE grade                    | -                        | -           | 0W30         |
| Density at 15°C              | kg/m <sup>3</sup>        | NFT 60101   | 844          |
| Kinematic viscosity at 40°C  | mm <sup>2</sup> /s (cSt) | NFT 60100   | 62,68        |
| Kinematic viscosity at 100°C | mm <sup>2</sup> /s (cSt) | NFT 60100   | 11,5         |
| Viscosity index              | -                        | NFT 60136   | 178          |
| Dynamic viscosity at -30°C   | mPa.s                    | ASTM D 5293 | 5920         |
| Sulphated ash content        | % weight                 | NF T 60143  | 0,76         |
| Pour point                   | °C                       | NFT 60105   | -45          |
| Flash point                  | °C                       | NFT 60118   | 239          |
| TBN (Total Base Number)      | mg KOH/g                 | ASTM D 2896 | 6,6          |

*The average values are given for information only.*