

OPALJET MILLENIUM 4

100% Synthetic oil "FUEL ECONOMY" for PSA

120048/02.24

Rev. 1

DESCRIPTION & APPLICATIONS

OPALJET MILLENIUM 4 5W30 is designed to save fuel (up to 8% on some PSA models) and extend the life of aftertreatment systems.

OPALJET MILLENIUM 4 5W30 is a low SAPS oil intended for engines equipped with particulate filters and Euro 5 emission standards.

OPALJET MILLENIUM 4 5W30 has been developed for Peugeot and Citroen vehicles to solve LSPI (low speed ignition) problems.

OPALJET MILLENIUM 4 5W30 is recommended for vehicles meeting the C2 standard in class 5W30 such as certain FIAT, IVECO, HONDA engines.

ADVANTAGES

- OPALJET MILLENIUM 4 protects particulate filters against pollution.
- Maximum protection of particulate filters against fouling.
- Low volatility and incisable thanks to its 100% synthetic nature.
- Excellent resistance to oxidation thanks to the nature of the base oils
- Extremely detergent: maintains the cleanliness of all the parts of your engine, preventing the formation of deposits at high and low temperatures.
- Reduces the problem of low speed pre-ignition (LSPI)

PERFORMANCES

Satisfies to the following specifications:

ACEA C2-16

API CF/SN

FIAT 9,55535-S1/G1

IVECO 18-1811 SC1

PSA B 71 2290-17

OPALJET MILLENIUM 4

ENVIRONMENT, HEALTH & SAFETY

Please consult also the Safety Data Sheet about how to manipulate and to stock the product as well as to learn about the first aid measurements in case of accident.

Elimination after use must be made in conformity with the local rules in force about used oils disposal. When needed, Safety Data Sheet can be obtained upon request.

Conservation of the product: 3 year(s) in closed container and sheltered.

PROPERTIES

CHARACTERISTICS	UNITS	METHODS	TYPICAL DATA
SAE grade	-	-	5W30
Density at 15°C	kg/m ³	NFT 60101	852
Kinematic viscosity at 40°C	mm ² /s (cSt)	NFT 60100	57,1
Kinematic viscosity at 100°C	mm ² /s (cSt)	NFT 60100	10,1
Viscosity index	-	NFT 60136	167
Dynamic viscosity at -30°C	mPa.s	ASTM D 5293	5460
Flash point	°C	NFT 60118	232
Pour point	°C	NFT 60105	-39
Noack evaporation loss	% weight	CEC-L-40-T-87	10,1
Sulphated ash content	% weight	NF T 60143	0,8

The average values are given for information only.