

OPALJET POWER FE 950 0W30

100% SYNTHETIC OIL FOR PETROL AND DIESEL ENGINES

120073/01.24

Rev. 2

DESCRIPTION & APPLICATIONS

OPALJET POWER FE 950 0W30 is a fully synthetic oil, MID SAPS Fuel Eco, developed mainly for Ford Duratorq TDCI Euro6 engines (from 2014) with exhaust gas post-treatment systems and a turbocharger requiring the FORD WSS M2C950-A specification.

OPALJET POWER FE 950 0W30 was developed primarily for the latest FORD engines, but it is also suited to engines of vehicles requiring a level of viscosity of 0W30 and ACEA C2-16 performance levels (Fiat, Alfa Romeo, Mitsubishi, Subaru, Suzuki, Toyota, ect.).

Approvals
Ford WSS-M2C-950A

ADVANTAGES

- A broad running range thanks to its high viscosity index (VI), hence allowing oil change intervals to be extended safely.
- An exceptional oil film resistance at high temperature for better oil consumption control and reduced wear thanks to its excellent lubricating properties.
- A MID SAPS technology (low ash, sulphur, and phosphorus content) extending the lifetime of particle filters (FAP) and enhancing catalyst protection.
- A low cold viscosity (SAE 0W grade) allowing the lubricant to flow more rapidly in the engine, hence limiting metal-metal contacts to optimize fuel savings and improve the reduction of CO2 emissions while ensuring excellent wear protection of the engine.
- Exception engine cleanliness and good protection of the chain thanks to its anti-wear, anti-corrosion and anti-foaming properties.
- OPALJET POWER FE 950 0W30 also allows biofuels to be used without altering the performance of the lubricant.

PERFORMANCES

Satisfies to the following specifications:

ACEA C2-16
FORD M2C-950A
FIAT 9.55535 GS1/DS1

OPALJET POWER FE 950 0W30

ENVIRONMENT, HEALTH & SAFETY

Please consult also the Safety Data Sheet about how to manipulate and to stock the product as well as to learn about the first aid measurements in case of accident.

Elimination after use must be made in conformity with the local rules in force about used oils disposal. When needed, Safety Data Sheet can be obtained upon request.

Conservation of the product: 3 year(s) in closed container and sheltered.

PROPERTIES

CHARACTERISTICS	UNITS	METHODS	TYPICAL DATA
SAE grade	-	-	0W30
Density at 20°C	kg/m ³	NFT 60101	841
Kinematic viscosity at 40°C	mm ² /s (cSt)	NFT 60100	50
Kinematic viscosity at 100°C	mm ² /s (cSt)	NFT 60100	9,7
Viscosity index	-	NFT 60136	186
Pour point	°C	NFT 60105	-51
Flash point	°C	NFT 60118	226
Noack evaporation loss	% weight	CEC-L-40-T-87	11,5
Sulphated ash content	% weight	NF T 60143	0,87
Viscosity CCS at -35°C	mPa.s	ASTM D 5293	5932
TBN (Total Base Number)	mg KOH/g	ASTM D 2896	8

The average values are given for information only.