



SEALAX 22

Ind. Diverse, Rubber

MINERAL

U230602

16/02/2026

Proces oil Rubber industry

V26.2

DESCRIPTION

Highly refined naphthenic oil used as a plasticizer in the manufacture of rubbers.

ADVANTAGES

- Good solvent power.
- Compatible with polychloroprene, SIS, SBR, NR, BR, IR and NBR.

SPECIFICATIONS

ACEA: -, API: -,
NORMS / APPROVALS:
SPECIFICATIONS:

RECOMMENDATIONS: plasticine film on rubber, Lost lubrication

AVAILABILITY

U230602	Bulk	IBC	Barrel	60L/53kg	20L steel	20L/ 18 kg plastic	4X5L	12X1L Specials	small / 400 gr
	/99	/97	/68	/42	/41	/29	/5	/12	

SEALAX 22

TECHNICAL DATA

-----E230602

PROPERTIES	UNIT	METHOD	VALUE
ACEA	Association Constructeurs Européennes de l'Automobile		-
API	American Petroleum institute		-
SAE / ISO-VG / NLGI			22
Colour	Visual		
Density @ 15°C	kg / L	ASTM D1298	0.900
Pourpoint	°C	ASTM D97	-33
Flashpoint COC	°C	ASTM D92	165
Kinematic Viscosity @40°C	cSt	ASTM D7279	22
Kinematic viscosity @ 100°C	cSt	ASTM D7279	
(V.I.) Viscosity index		ASTM D2270	
Copper Corrosion		ASTM D130	
Anilinepoint	°C	ASTM D611	
Noack evap	% w/w	ASTM D 5800	
TAN	mg KoH/g	ASTM D 664	0.03
Sulphated Ash	% weight		
Storage of the product: (Shelf life)	Years	in a sheltered environment, unopened.	3

For guidelines on emergencies, handling and storage etc., please refer to the SDS/MSDS. This is available on request.

Any handling/disposal/liquidation of the product must comply with local regulations for petrochemicals. Advice will be given on request.