



SYNGREEN GREASE (50kg)

Grease, Biodegradable

SYNTH ESTER

U310030

3/25/2025

V 25,2

Anhydrous calcium grease 50 kg

DESCRIPTION

SYNGREEN GREASE is a biodegradable extreme pressure grease, for all applications.

The thickener, combined with the base oil mixture, makes it a grease suitable for various applications within the given temperature limits.

This lubricating grease offers good mechanical stability, good resistance to loads and good protection against corrosion.

SYNGREEN GREASE is particularly recommended for lubricating small forestry maintenance equipment, landscaping equipment, etc.

ADVANTAGES

EAL (Environmentally Acceptable lubricant).

- Excellent water resistance.

- Easily pumpable.

NORMS

/APPROVALS

Lithium-Calcium

SPECIFICATIONS

EAL (Environmentally Acceptable Lubricant), -20°C - 100°C, Volvo Trucks General Grease

RECOMMENDATIONS

OECD 301B, Swedish Standard 155470

AVAILABILITY

	Bulk	IBC	Barrel	60L/53kg	20L steel	20L/ 18 kg plastic	4X5L	12X1L Specials	small / 400 gr
U310030			U310098	U310030		U310016			U310104

SYNGREEN GREASE (50kg)

TECHNICAL DATA

-----E310030

PROPERTIES	UNIT	METHOD	VALUE
ACEA	Association Constructeurs Européennes de l'Automobile		
API	American Petroleum institute		
SAE / ISO-VG / NLGI			NLGI 2
COLOUR	Visual		GREEN
Density @ 15°C	kg / L	ASTM D1298	
Pourpoint	°C	ASTM D97	
Flashpoint COC	°C	ASTM D92	
Cinematic Viscosity @40°C	cSt	ASTM D7279	130 (oil)
Kinematic viscosity @ 100°C	cSt	ASTM D7279	23
(V.I.) Viscosity index		ASTM D2270	
Copper Corrosion		ASTM D130	
Anilinepoint	°C	ASTM D611	
Noack evap	% w/w	ASTM D 5800	
4 ball weld load	Kgf	ASTM D 2596	285
DROPPING POINT	°C	ASTMD 2265	160
Sulphated Ash	% weight		
Waterwashtest	% @ 39 °C	ASTM D 2164	0/1
Penetration 60 strokes @ 25°C	1/10mm	ISO 2137	265-295

For guidelines on emergencies, handling and storage etc., please refer to the SDS/MSDS. This is available on request. Storage of the product: 3 years in a sheltered environment, unopened.

Any handling/disposal/liquidation of the product must comply with local regulations for petrochemicals. Advice will be given on request.